

# WEDOLiT AS 4116

**High-Protection-DW-Fluid 60°C flash point**  
(aromatic content  $\leq$  2%)



WEDOLiT AS-4116 is a leading edge corrosion inhibitor for steel and other metals, which offers long-term protection for indoor storage. Its low viscosity allows it to be used as an immersion bath, e.g. for the treatment of hollow parts. It can also be applied by spraying, flooding, brushing or rolling.



## Physical Properties Typical Data

Parameter	Typical results	Tested according to
Appearance:	Medium-brown, clear	Visual
Density at 15°C:	0.81 g/cm <sup>3</sup>	ASTM D 7042
Viscosity at 20°C:	2.3 mm <sup>2</sup> /s	ASTM D 7042
Flash point:	> 60 °C	DIN EN ISO 2719
Film weight:	0.5 g/m <sup>2</sup>	Dipping procedure
Film type:	Microwax	Haptical
Dewatering effect:	30 s	Internal test method
Water separation:	4 min	Internal test method
Humidity test:	90 cycles	DIN EN ISO 6270-2 AHT
Salt spray performance:	24 h	DIN EN ISO 9227 NSS

## Application Guidelines

Storage must be frost-free between 5 - 35°C.

The minimum durability is 12 months in an original sealed package.

## Additional Information

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation, or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. For the most recent version of this document, please go to this URL: [https://2trim.us/diw/?plr=AS-4116\\*en-us\\*na](https://2trim.us/diw/?plr=AS-4116*en-us*na)

WEDOLiT AS 4116

©2018-2020 Master Fluid Solutions® | 2020-02-20


## Choose WEDOLiT AS 4116:


- Ideal for overseas transport
- Suitable for VCI-foils: The full corrosion protection is only given in the solvent-free film, therefore a short storage time until the solvent evaporates must be observed especially before packing in boxes with foils
- Stable against acidic and alkaline contamination
- Good material compatibility
- Water displacing with very good wetting behavior
- Easily removable with organic solvents (cold cleaners) or water-miscible alkaline industrial cleaners
- Additive loss due to water contact: Extremely low


## Health and Safety


For further information, see the most recent SDS which is available directly from Master Fluid Solutions.



 501 West Boundary Street  
Perrysburg, OH 43551-1200  
USA

 +1 419-874-7902

 [info@masterchemical.com](mailto:info@masterchemical.com)

 [masterfluidsolutions.com/na/en-us/](https://masterfluidsolutions.com/na/en-us/)